

TECH LINE COATINGS, INC.



26844 ADAMS AVE. ♦ MURRIETA, CA 92562 ♦ USA
PHONE 909-304-0498
♦ FAX 909-461-9658

WWW.TECHLINECOATINGS.COM

TECHTREX™ 75000 SERIES

PRODUCT DATA SHEET: 75000 HIGH PRESSURE LUBRICATION SELECTION DATA

CHEMICAL NAME / SYNONYMS:

POLYARYLEETHERKETONE/POLYETHERETHERKETONE

PRODUCT DESCRIPTION:

TECHTREX™ 75000 series thermoplastic coatings are formulated from Victrex® PEEK™. In a thin film TECHTREX™ 75000 allows a user to benefit from the advanced performance benefits commonly found in molded PEEK, with the added benefits of **Extreme Pressure Lubricants**, in a spray applied coating. TECHTREX™ has excellent Chemical, Tribological, and Corrosion resistance, in one package. In addition the Physical properties of the Victrex® PEEK™ polymer have raised it to the premier position among thermoplastics.

TECHTREX™ is a water dispersed coating. Easily sprayed with conventional spray equipment.

RECOMMENDED USES:

TECHTREX™ can be used in a wide range of applications; Automotive, Aerospace, Fluid Transfer, Food Handling and Processing, Industrial, Marine, Oil and Gas Exploration, to name just a few.

Not for human implantation. Not recommended for Medical use.

TECHTREX™ 75000 series can be compounded with a wide variety of other lubricating materials.

NOT RECOMMENDED FOR: Any substrate that cannot handle the required 750 °F cure.

CHEMICAL RESISTANCE GUIDE:

Exposure	Splash	Fumes
Acids	Excellent	Excellent
Alkaline	Excellent	Excellent
Solvent	Excellent	Excellent
Fluids	Excellent	Excellent
Fuels	Excellent	Excellent
Salt	Excellent	Excellent
Water	Excellent	Excellent

(See Chemical Resistance Chart for greater detail)

TEMPERATURE RESISTANCE: Continuous to 500°F.

FLEXIBILITY: Very Good **WEATHERING:** Good

ABRASION RESISTANCE: Excellent

SUBSTRATES: May be applied to both ferrous and non-ferrous.

TOPCOAT REQUIRED: None Required

SPECIAL TREATMENT: None

COMPATIBILITY WITH OTHER COATINGS: TECHTREX™ 71000 may be used as a build-up base for TECHTREX™ 75000 series coatings.

SPECIFICATION DATA

THEORETICAL SOLIDS CONTENT OF MIXED MATERIAL: @ 38% WT

RECOMMENDED DRY FILM THICKNESS PER COAT: .001" to .0015"

THEORETICAL COVERAGE:

BURNISHING: None required.

SHELF LIFE: 1 year plus.

COLOURS: Dark Gray to Black for the Standard material.

GLOSS: Medium

ORDERING INFORMATION

Prices may be obtained from Tech Line Coatings, Inc. sales representative or main office.

APPROXIMATE SHIPPING WEIGHT:

TECHTREX™ 75000 (1 gallon) = 4.1 Kilograms (9.0 lbs. US)

FLASH POINT: 0

SURFACE PREPARATION: All parts must be absolutely free of all oils, grease, moisture, dust, scale or corrosion.

METALS: For steel, sandblast with 80-100 grit aluminum oxide or similar. Softer metals, such as aluminum, use 100-120 grit aluminum oxide or similar at 35-40 PSI using a suction type blaster.

FINAL CLEAN: Before spraying the part must be thoroughly cleaned using air blast, hot water rinse, solvent base rinse, DO NOT USE petroleum based solvents, or any other method that provides a clean dry surface.

MIXING: Stir well. Disperse all solids that may have settled to the bottom of the container.

PRIMER: No primer needed.

APPLICATION TEMPERATURES:

	<u>Material</u>	<u>Surfaces</u>	<u>Ambient</u>	<u>Humidity</u>
Normal	18-30°C	18-30°C	16-32°C	35-85%
Minimum	13°C	13°C	10°C	30%
Maximum	35°C	38°C	38°C	95%

SPRAY: Apply coating in light fog passes (approximately 10% overlap) to achieve a thickness of .001” to .0015”. Use sufficient air volume for correct operation of equipment. (Minimum 40 PSI to a maximum of 65 PSI) Minimum part temperature should be 55F or above. Spray at a right angle to part with a 1mm or smaller nozzle size. Spray all irregular surfaces and edges first, making an extra pass later. Check part for complete coverage. Part should be a gray/black color.

GUN & Mfr.: Any conventional unit. Recommended gravity feed type touch-up gun. (Important that nozzle size be 1mm or less)

DRYING TIME: Allow coating to air dry for at least 10 minutes at ambient. If top coating “flash” at 150f for 10 minutes after the air dry period has elapsed.

FINAL CURE: 750F for 20 minutes at temperature. Place dry coated part directly into the oven at cure temperature.

Multi Coating: Multiple coats of TECHTREX™ are possible. Bring an initial coat of 71000 to 710f for 10 minutes or until the coating gives evidence of beginning to "melt" and shows a darker color. Remove room the oven all to cool and apply a second coat. Repeat this process until the desired thickness is reached and then full cure at 750f. When it is desirable to apply a "filled" TECHTREX™ formula, such as #75000, TECHTREX™ 71000 should be used for the build coats and the final layer should be the "filled" formulation.

VENTILATION AND SAFETY: When used in enclosed areas, thorough air circulation must be provided during and after application until the coating is cured. The ventilating system should be capable of preventing fine particulate matter from exceeding TLV limits.

CLEAN UP: Water

STORAGE CONDITIONS: (Store indoors)
Temperature: 10-43°C Humidity: 0-100%

THIS INFORMATION IS FURNISHED WITHOUT WARRANTY, REPRESENTATION, INDUCEMENT OR LICENSE OF ANY KIND, EXCEPT THAT IT IS ACCURATE TO THE BEST OF TECH LINE COATINGS, INC., KNOWLEDGE OR OBTAINED FROM SOURCES BELIEVED BY TECH LINE COATINGS, INC. TO BE ACCURATE, AND TECH LINE COATINGS, INC., DOES NOT ASSUME ANY LEGAL RESPONSIBILITY FOR USE OR RELIANCE UPON SAME. BEFORE USING ANY CHEMICAL, READ ITS LABEL, INSTRUCTIONS AND MATERIAL SAFETY DATA SHEET.

Note: N/E = Not Established
N/A = NO APPLICABLE



These instructions are not intended to show product recommendations for specific service. They are issued as an aid in determining correct surface preparation, mixing instructions and application procedure. It is assumed that the proper product recommendations have been made. Those instructions should be followed closely to obtain the maximum service from the materials.